

U.S. PTO
09/680401
10/05/00

**UTILITY
PATENT APPLICATION
TRANSMITTAL**

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Attorney Docket No. 198224US0X
First Inventor or Application Identifier Seinosuke MIZUNO, et al.
Title SHRINKAGE CONTROL MATERIAL AND ELASTOMERIC MOLDING

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents

ADDRESS TO: Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

Fee Transmittal Form (e.g. PTO/SB/17)
(Submit an original and a duplicate for fee processing)

2. ☒ Specification Total Pages **13**
3. ☒ Drawing(s) (35 U.S.C. 113) Total Sheets **1 (Formal)**
4. ☐ Oath or Declaration Total Pages
a. ☐ Newly executed (original or copy)
b. ☐ Copy from a prior application (37 C.F.R. §1.63(d))
(for continuation/divisional with box 15 completed)
i. ☐ DELETION OF INVENTOR(S)
Signed statement attached deleting inventor(s) named
in the prior application, see 37 C.F.R. §1.63(d)(2) and
1.33(b).
5. ☐ Incorporation By Reference (usable if box 4B is checked)
The entire disclosure of the prior application, from which a copy of the
oath or declaration is supplied under Box 4B, is considered to be part
of the disclosure of the accompanying application and is hereby
incorporated by reference therein

ACCOMPANYING APPLICATION PARTS

6. ☐ Assignment Papers (cover sheet & document(s))
7. ☐ 37 C.F.R. §3.73(b) Statement ☐ Power of Attorney
(when there is an assignee)
8. ☐ English Translation Document (if applicable)
9. ☒ Information Disclosure Statement (IDS)/PTO-1449 ☒ Copies of IDS Citations (1)
10. ☐ Preliminary Amendment
11. ☒ White Advance Serial No. Postcard
12. ☐ Small Entity Statement(s) ☐ Statement filed in prior application. Status still proper and desired.
13. ☐ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
14. ☒ Other: Notice of Priority, List of Inventors' Names and Addresses

15. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application no.:
Prior application information: Examiner: Group Art Unit:

16. Amend the specification by inserting before the first line the sentence:

- ☐ This application is a ☐ Continuation ☐ Division ☐ Continuation-in-part (CIP)
of application Serial No. Filed on
- ☐ This application claims priority of provisional application Serial No. Filed

17. CORRESPONDENCE ADDRESS



22850

(703) 413-3000
FACSIMILE: (703) 413-2220

Name:	Norman F. Oblon	Registration No.:	24,618
Signature:		Date:	10/5/00
Name:	C. Irvin McClelland	Registration No.:	

Registration Number 21,124

Docket No. 198224US0X

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

INVENTOR(S) Seinosuke MIZUNO, et al.

SERIAL NO: New Application

FILING DATE: Herewith

FOR: SHRINKAGE CONTROL MATERIAL AND ELASTOMERIC MOLDING

jc675 U.S. PTO
09/680401
10/05/00

FEE TRANSMITTAL

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

FOR	NUMBER FILED	NUMBER EXTRA	RATE	CALCULATIONS
TOTAL CLAIMS	8 - 20 =	0	× \$18 =	\$0.00
INDEPENDENT CLAIMS	2 - 3 =	0	× \$80 =	\$0.00
<input type="checkbox"/> MULTIPLE DEPENDENT CLAIMS (If applicable)			+ \$270 =	\$0.00
<input checked="" type="checkbox"/> LATE FILING OF DECLARATION			+ \$130 =	\$130.00
BASIC FEE				\$710.00
TOTAL OF ABOVE CALCULATIONS				\$840.00
<input type="checkbox"/> REDUCTION BY 50% FOR FILING BY SMALL ENTITY				\$0.00
<input type="checkbox"/> FILING IN NON-ENGLISH LANGUAGE			+ \$130 =	\$0.00
<input type="checkbox"/> RECORDATION OF ASSIGNMENT			+ \$40 =	\$0.00
TOTAL				\$840.00

- ☐ Please charge Deposit Account No. 15-0030 in the amount of _____ A duplicate copy of this sheet is enclosed.
- ☒ A check in the amount of **\$840.00** to cover the filing fee is enclosed.
- ☒ The Commissioner is hereby authorized to charge any additional fees which may be required for the papers being filed herewith and for which no check is enclosed herewith, or credit any overpayment to Deposit Account No. 15-0030. A duplicate copy of this sheet is enclosed.

Respectfully Submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.

Date: _____

10/5/00

Norman F. Oblon

Registration No. 24,618

C. Irvin McClelland
Registration Number 21,124



22850

Tel. (703) 413-3000
Fax. (703) 413-2220
(OSMMN 10/00)

Docket No. 198224US0X

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

IN RE APPLICATION OF: Seinosuke MIZUNO, et al.

FILING DATE: Herewith

FOR: SHRINKAGE CONTROL MATERIAL AND ELASTOMERIC MOLDING



LIST OF INVENTORS' NAMES AND ADDRESSES

ASSISTANT COMMISSIONER FOR PATENTS
WASHINGTON, D.C. 20231

SIR:

Listed below are the names and addresses of the inventors for the above-identified patent application.

Seinosuke MIZUNO	Tokyo, JAPAN
Yoshiyuki NISHI	Tokyo, JAPAN
Yasunari ASHIDA	Tokyo, JAPAN
Tatsumi HIRANO	Tokyo, JAPAN

A declaration containing all the necessary information will be submitted at a later date.

Respectfully Submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.

Norman F. Oblon

Registration No. 24,618

C. Irvin McClelland
Registration Number 21,124



22850

Tel. (703) 413-3000
Fax. (703) 413-2220
(OSMMN 11/98)

005001-10000000

SHRINKAGE CONTROL MATERIAL AND ELASTOMERIC MOLDING

Background of the Invention

1. Field of the Invention

5 The present invention relates to a shrinkage control material used for various kinds of molding, a door window glass run channel or the like for automobiles, and bead material for window frames or the like for buildings, and to a elastomeric molding using the same.

10 2. Description of the Related Art

Various kinds of molding and window door glass run channel for automobiles, window frame beads for buildings or the like are generally formed of rubber or resin by means of extrusion.

15 In the extrusion products of rubber or resin as mentioned above, in order to prevent the rubber or resin from shrinking to deform due to temperature variation during molding or use, a resilient metal wire is used to bury. In burying the wire, it is general that the metal wire is passed
20 through a coater to coat an adhesive around an outer periphery thereof. Thereafter, while introducing the adhesive coated metal wire into an extruder, around the outer periphery thereof rubber or resin is extruded.

However, in the method like this, there is a problem
25 that the adhesive coater is necessary to be disposed before the extruder to result in a complicated process control.

To this problem, a shrinkage control material or a reinforcement material has been developed in which, on a

surface of a metal wire, melt-bonding varnish is coated and baked in advance to dispose a melt-bonding layer.

According to the shrinkage control material, due to heat during extrusion of the rubber or resin, the hot-melt layer is once melted, thereafter together with the rubber or resin being cooled to solidify into one body. Accordingly, the adhesive coater is not required to be disposed ahead of the extruder.

For the melt-bonding varnish to be coated on the surface of the metal wire, so far the melt-bonding varnish based on polyester resin is generally used.

However, the polyester resin based varnish is a little weaker in adhesion to the rubber than to the resin. Accordingly, there is a problem that the shrinkage control material using the polyester resin based melt-bonding varnish can not exhibit an expected shrinkage prevention effect in a rubber molding.

Accordingly, a shrinkage control material that is excellent in adhesion to the rubber and can exhibit a sufficient shrinkage prevention effect to the rubber is desired to develop.

Summary of the Invention

It is an object of the present invention is to provide a shrinkage control material that is excellent in adherence with elastomeric material and can exhibit a sufficient shrinkage prevention effect to elastomeric material, and an elastomeric molding with the shrinkage control material.

According to one aspect of invention, a shrinkage control material includes a resilient metal wire, and an adhesive layer coated and heated on the metal wire, the adhesive layer having adhesion to elastomeric material.

5 The adhesive layer preferably comprises a halogenated polymer- or olefin-based adhesive.

According to another aspect of invention, an elastomeric molding comprises a shrinkage control material, and an elastomeric extrusion formed around an outer periphery
10 of the shrinkage control material. The shrinkage control material includes a resilient metal wire, and an adhesive layer coated and heated on the metal wire, the adhesive layer having adhesion to elastomeric material. The elastomeric extrusion is bonded by vulcanization to the shrinkage control
15 material.

The adhesive layer preferably comprises a halogenated polymer- or olefin-based adhesive.

According to an aspect of the present invention, the adhesive layer of a shrinkage control material has adhesion
20 to various kinds of elastomeric material. That is, due to heat, pressure or the like during extrusion and vulcanization of an elastomeric material, the adhesive layer is vulcanized to bond solidly the metal wire to the elastomeric material, followed by cooling to solidify into one body. Therefore,
25 the shrinkage control material can be applied to various kinds of elastomeric material to exhibit an excellent shrinkage prevention effect. The adhesive layer of halogenated polymer- or olefin-based adhesive has excellent

adhesion to the various kinds of elastomeric material. The shrinkage control materials using them can prevent the shrinkage more effectively.

5 Brief Description of the Drawings

Fig. 1 is a cross sectional view of an embodiment of a shrinkage control material of the present invention.

Fig. 2 is a perspective view of an embodiment of a rubber molding of the present invention having the shrinkage control material of Fig. 1.

10 Detailed Description of Preferred Embodiments

In the following, Embodiments of the present invention will be detailed with reference to the drawings.

15 Referring to Fig. 1 of the drawings, there is shown an embodiment of a shrinkage control material of the present invention indicated generally by the numeral 10.

20 The shrinkage control material 10 comprises a resilient metal wire 12 generally circular in cross section, and an adhesive layer 14 coated and heated on the the metal wire 12, the adhesive layer 14 having a halogenated polymer- or olefin-based adhesive.

25 The resilient metal wire 12 will be made of brass, iron, iron alloy, steel such as stainless steel, phosphor bronze, nickel silver or the like. Iron and iron alloy are preferable to implement brass plating, zinc plating, or other suitable plating on the surface thereof to use, for they tend to be oxidized in the air to be brittle.

The metal wire 12, without restricting to one of circular cross-section mentioned in the embodiment, may be one configured in other cross-section such as pillar shape. Alternatively, the metal wire 12 may be formed in a structure where a plurality of metal wires of circular cross-section is stranded. Further, in order to improve adherence to the rubber described later, a surface can be roughened, or corrugated in a longer length direction.

The adhesive layer 14 is preferably formed by coating and heating the halogenated polymer- or olefin-based adhesive, or other adhesive on an outer periphery of the metal wire 12. The adhesive layer 14 formed thus does not show tackiness at normal temperature but it shows adhesion when vulcanized by heating under pressure.

A preferred halogenated polymer-based adhesive is one comprising a chlorinated rubber and a chlorosulfonated polyethylene rubber, such as THIXON GPO (trade name) by Morton International Co. or Metalock F-10 (trade name) by Toyo Kagaku Kenkyusho. A preferred olefin-based adhesive is Chemlok 238, 250, 250X (all trade names) by Road Far East Inc. or TPO-300 (trade name) by The Yokohama Rubber Co., Ltd.. Furthermore, a thickness of the adhesive layer 14, when EPDM (ethylene-propylene-diene ternary copolymer) rubber is extruded on the layer 14 and THIXON GPO is used as the adhesive, is preferably in the range of 5 to 25 μ m, more preferably in the range of 12 to 22 μ m. When the thickness of the layer 14 is less than 5 μ m or exceeds 25 μ m, it will not show enough adhesion strength to prevent the shrinkage of

the EPDM rubber.

The shrinkage control material 10 comprises the metal wire 12 and the adhesive layer 14. The adhesive layer 14, when a elastomeric material such as EPDM rubber is extruded thereon, is vulcanized together with the elastomeric material under heat and pressure during extrusion and vulcanization to strongly bond the elastomer extrusion to the metal wire 12. Thereafter, the adhesive layer 14 is cooled with the elastomeric extrusion to solidify to exhibit excellent shrinkage prevention effect to various kinds of elastomeric molding.

Fig.2 is a perspective view of one example of an automobile window molding with the shrinkage control material 10. Inside the extrusion 20 of an elastomeric material such as EPDM rubber that is extruded in a prescribed sectional shape and vulcanized, the shrinkage control material 10 is buried. The metal wire 12 and the elastomeric extrusion 20 are bonded through the adhesive layer 14 of the shrinkage control material 10.

A material of the elastomeric extrusion 20 may be ethylene propylene copolymer rubber, natural rubber, styrene rubber, chloroprene rubber, buthyl rubber, or nitrile rubber. In a preferred embodiment, the material of the elastomeric extrusion 20 is EPDM rubber.

The window molding will be produced by introducing the shrinkage control material 10 into an extruder, and extruding a material of the extrusion 20 around the shrinkage control material 10 to vulcanized. The adhesive layer 14 of the

shrinkage control material 10 is vulcanized under heat and pressure during extrusion or vulcanization to be cooled/cured in one body together with the elastomeric extrusion 20.

Thereby, the metal wire 12 and the elastomeric extrusion 20 are strongly bonded to be sufficiently suppressive of shrinkage or deformation in a longer length direction of the elastomeric extrusion 20 due to temperature variation.

More than one shrinkage control material may be buried in the elastomeric extrusion 20.

The invention will now be explained in more detail by way of the following non-limiting examples, in which all Young's modulus values are values measured under gauge length of 25mm, tensile testing speed of 1mm/min, and 2.5% elongation according to JIS K 7113.

Example 1

On a brass plated stainless steel wire of a diameter of 0.25mm, THIXON GPO was coated and baked to be a layer thickness of 9 μ m after baking, thereby obtaining a shrinkage control material.

Next, while introducing the obtained shrinkage control material into the extruder, around the shrinkage control material, EPDM was extruded to cover, thereby an automobile window molding as shown in Fig.2 being manufactured.

Examples 2 to 4

By implementing identically with Example 1 other than changing the thickness of the adhesive layer after baking to 14 μ m (Example 2), 18 μ m (Example 3) or 21 μ m (Example 4), shrinkage control materials were obtained. Further, with

these shrinkage control materials, as identical as Example 1, automobile window moldings were manufactured.

Comparative Example 1

By implementing identically with Example 1 other than changing the adhesive to TCV PA-18A (Totoku Toryo Co., Ltd.) that is a polyester-based adhesive, a shrinkage control material was obtained. Further, with this shrinkage control material, as identical as Example 1, an automobile window molding was manufactured.

Comparative Examples 2 to 4

By implementing identically with Comparative Example 1 other than changing the thickness of the adhesive layer after baking to $14\mu\text{m}$ (Comparative Example 2), $18\mu\text{m}$ (Comparative Example 3) or $21\mu\text{m}$ (Comparative Example 4), shrinkage control materials were obtained. Further, with these shrinkage control materials, as identical as Comparative Example 1, automobile window molding were manufactured.

With these window moldings obtained in the aforementioned examples and comparative examples, adhesive strength between the shrinkage control material and the EPDM extrusion was measured by means of the pultrusion method. The results and the configurations of the adhesive layers are shown in Table.

Table 1

	Kind of adhesive *	Thickness of adhesive layer (μ m)	Adhesive strength (kgf)	Remarks
Example 1	THIXON GPO	9	7.7	
Example 2	THIXON GPO	14	11.9	
Example 3	THIXON GPO	18	12.3	broken
Example 4	THIXON GPO	21	10.4	
Example 5	Chemlock250X	9	3.5	
Example 6	Chemlock250X	14	5.4	
Example 7	Chemlock250X	18	5.5	
Example 8	Chemlock250X	21	4.7	
Example 9	TPO-300	9	2.8	
Example 10	TPO-300	14	4.3	
Example 11	TPO-300	18	4.4	
Example 12	TPO-300	21	3.8	
Comparative Example 1	TCV PA-18A	9	≤ 1.0	
Comparative Example 2	TCV PA-18A	14	≤ 1.0	
Comparative Example 3	TCV PA-18A	18	≤ 1.0	
Comparative Example 4	TCV PA-18A	21	≤ 1.0	

* THIXON GPO: Product of Morton International Co.

Chemlock 250X: Product of Road Far East Inc..

TPO-300: Product of The Yokohama Rubber Co., Ltd.

TCV PA-18A: Product of Totoku Toryo Co., Ltd.

As obvious from the Examples mentioned above, according to the present invention, adhesive strength of a shrinkage control material to the elastomeric extrusion improved.

Therefore, with the shrinkage control material, an elastomeric molding slight in shrinkage or deformation during molding or due to temperature variation thereafter can be obtained.

While there has been shown and described what are at present considered the preferred embodiments of the invention, it will be obvious to those skilled in the art that various changes and modifications may be made therein without departing from the scope of the invention as defined by the appended claims.

What is claimed is:

1. A shrinkage control material comprising:

a resilient metal wire; and

an adhesive layer coated and heated on the metal wire,

5 the adhesive layer having adhesion to elastomeric material.

2. The shrinkage control material as set forth in
claim 1:

wherein the adhesive layer comprises a halogenated
polymer-based or olefin-based adhesive.

10 3. The shrinkage control material as set forth in
claim 1:

wherein the adhesive layer comprises chlorinated rubber
and sulfonated polyethylene rubber.

15 4. The shrinkage control material as set forth in
claim 1:

wherein the metal wire comprises one component selected
from brass, iron, iron alloy, steel, phosphor bronze and
nickel silver.

20 5. The shrinkage control material as set forth in
claim 1:

wherein the metal wire is a brass wire or a brass-
plating wire.

6. A elastomeric molding comprising:

a shrinkage control material having:

25 a resilient metal wire; and

an adhesive layer coated and heated on the metal wire,
the adhesive layer having adhesion to elastomeric material;
and

a elastomeric extrusion formed around an outer periphery of the shrinkage control material to cover, the elastomeric extrusion being bonded by vulcanization to the shrinkage control material.

5 7. The elastomeric molding as set forth in claim 6:

 wherein the adhesive layer comprises a halogenated polymer-based or olefin-based adhesive.

 8. The elastomeric molding as set forth in claim 6:

 wherein the adhesive layer comprises chlorinated rubber
10 and sulfonated polyethylene rubber.

Abstract of the Disclosure

A shrinkage control material for elastomeric molding.
On a surface of a resilient metal wire, an adhesive layer of
a halogenated polymer-based or olefin-based adhesive is
5 disposed. An elastomeric molding includes the shrinkage
control material and a elastomeric extrusion formed around
the shrinkage control material to cover, the elastomeric
extrusion being bonded by vulcanization to the shrinkage
control material.

FIG. 1




FIG. 2

